



QUALITY MANAGEMENT
SYSTEM
CERTIFIED ISO 9001

TECHNICAL DATA SHEET

Series

60

FALCON

● SUMMARY

**SPRAYING MONOCOMPONENT VARNISH FOR POLYETHER
POLYURETHANE SOLES, EXCELLENT RESISTANCE TO ABRASION, VERY
HIGH FLESSIBILITY AND GOOD COVERING POWER**

● CHARACTERISTICS

– Form	liquid
– Viscosity Ford cup n° 2	72 seconds
– Density at 20°C	0,97
– Drying at 80°C	10 minutes
– Drying at 20°C	15 minutes

● APPLICATION

- Before the application make sure the sole surface is degreased, cleaned and dried
- to be applied by spray-gun, manually or by means of suitable machines
- so to improve the finish uniformity, the varnish penetration into the sole surface and for reducing the final drying time of the whole cycle, we suggest to heat the sole before and after the spraying operation
- avoid the soles accumulating after their coloration, as you can face sticking problems with a film rupture; we suggest to put the soles into the boxes the day after the varnishing

● COLOURS

● SOLVENTS

Use **SOLVENTE 31702** for thinnings and washings

● PACKING

Bucket of Kg. 20

● STORAGE

Shelf life: about 24 months if stored in well closed original packings in a dry and airy place.
Keep from freezing and extreme heat.

This information is to the best of our knowledge true and accurate. However, all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control.

31-05-04 FR/pm